

Description:

High-performance, flexible, water-resistant cementitious adhesive with extended open time and reduced slip for ceramic tiles and stones.

Fields of Application:

Interior and exterior floor and wall bonding of all types and sizes of ceramic tiles, natural stone, marble, granite, porcelain ceramic, clinker, cotto on cementitious renders, cementitious screeds, and concrete.

Bonding of all types and sizes of tiles and glass mosaics in swimming pools, Turkish baths, water tanks, basins, and any other wet places.

Bonding of ceramic tiles or granite on existing granite, ceramic, marble.

Bonding of tiles in places where sudden temperature changes occur, such as cold storage depots and over-floor heat installations.

Bonding of tiles in places subject to heavy traffic, like shopping malls, hospitals, schools.

Properties:

Perfect adherence.

Highly deformable, resistant to temperature changes.

Waterproofing.

Extended open time.

Can be applied on vertical surfaces, even for bonding heavy tiles without sagging.

Easily trowellable.

Storage:

Store in a dry medium. Do not stack more than 10 bags on top of each other.

Packaging:

25 kg multi-ply paper bags

Application:

- Substrates must be sound, free from oil, grease, and sufficiently dry. Cementitious substrates must be cured.

- Slowly pour 25 kg of POLYFLEX 61 into 5-5.5 liters of clean water and mix to obtain a homogeneous paste free from lumps. It is recommended to use a low-speed mixer for mixing. Do not add any additives that are not mentioned in the application instructions.

- Allow the mixture to stand for 5-10 minutes to mature. After 1-2 minutes of remixing, the paste is ready for application.

- Spread the mortar onto the substrate using a notched trowel with a notch size appropriate to the tile dimension (See Notch Size Recommendation Table). To achieve good adhesion, first apply a thin coat of POLYFLEX 61 with the flat side of the trowel, then notch it with the toothed side of the trowel. For large tiles, existing tiles, or tiles subject to frost or heavy traffic, apply POLYFLEX 61 on the back of the tiles as well (combined method).

- Wipe the backside of tiles with water if dusty.

- The open time is 30 minutes. Install the tiles within this period with firm pressure. Unfavorable climatic conditions such as high temperature, low humidity, wind, etc., can reduce this time to just a few minutes. If the open time is exceeded, scratch and discard the mortar.

- When using POLYFLEX 61 as both an adhesive and a water insulation material, apply mortar on both the substrate and the backside of the tiles (combined method). Alternatively, apply a layer of 1-2 mm of POLYFLEX 61 with reinforcement mesh at corners, then install the tiles after 24 hours.

- Dispose of mortars that have exceeded their pot life. Clean tools and hands with water, and surfaces with a damp cloth.

Tiles installed with POLYFLEX 61 must not be exposed to water for at least 24 hours.

Warnings:

- Since it contains cement, it can be irritating to the eyes, respiratory system, and skin. For further information, refer to the safety data sheet.

- The indicated consumption is general information and may change depending on the application conditions and surface properties.

Technical Properties		(at 23°C and 50% RH)
General Data		For POLYFLEX 61
Appearance		Grey Powder
Shelf Life		12 months when stored in original sealed packing in dry
Application Data		
Application Temperature Range		(+5°C) - (+35°C)
mixing Ratio		5-5.5 lt water / 25 kg powder / 2.5 - 2.75 / 12.5 kg
Port Life		Approximately 5 hrs
Slip (EN 1308)		≤0.5 mm
Open Time (EN 1346)		After 25 minutes ≥0.5 N/mm ²
Grouting		10 hours on wall 24 hours after on floor
Consumption		3.5 kg / m ²
Performance Data		
Tensile Adhesive Strength (EN 1348)		
Initial		≥1 N/mm ²
After Heat Exposure		≥ 1 N/mm ²
After Immersion In Water		≥ 1 N/mm ²
After Freeze/Thaw Cycles		≥ 1 N/mm ²
Deformability (EN 12002)		≥ 5 mm-S2 Highly Deformable
Service Temperature Range (After Final Cure)		(-40°C)-(+80°C)
Dangerous Substances (EN 12004)		Complies
Reaction To Fire		A1